

PAT. INFO.
IN 27 319679
NASA CASE NO. LAB-14036-1

PRINT FIG. No Figure P/0

NOTICE

The invention disclosed in this document resulted from research in aeronautical and space activities performed under programs of the National Aeronautics and Space Administration. The invention is owned by NASA and is, therefore, available for licensing in accordance with the NASA Patent Licensing Regulation (14 Code of Federal Regulations 1245.2).

To encourage commercial utilization of NASA-owned inventions, it is NASA policy to grant licenses to commercial concerns. Although NASA encourages nonexclusive licensing to promote competition and achieve the widest possible utilization, NASA will consider the granting of a limited exclusive license, pursuant to the NASA Patent Licensing Regulations, when such a license will provide the necessary incentive to the licensee to achieve early practical application of the invention.

Address inquiries and all applications for license for this invention to NASA Patent Counsel, Langley Research Center, Mail Code 279, Langley Station, Hampton, VA 23665. Approved NASA forms for application for nonexclusive or exclusive license are available from the above address.

Serial Number 418,372
Filed Date: October 6, 1989

LaRC

(NASA-Case-LAR-14036-1) TISSUE SIMULATING
GEL FOR MEDICAL RESEARCH Patent Application
(NASA) 10 p CSCL 11C

N91-13562

Unclas

63/27 0319679

TISSUE SIMULATING GEL FOR MEDICAL RESEARCH

Awards Abstract

LAR 14036-1

This invention discloses a tissue simulating gel and a method for preparing it. The process combines water, gelatin, ethylene glycol, and a cross-linking agent. The process also allows for the addition of material to modify the electrical, sound conducting, and wave scattering properties of the tissue simulating gel. The result of the entire process is a formulation that will not melt at the elevated temperatures involved in hyperthermia medical research. Additionally, the disclosed tissue simulating gel will not support mold or bacterial growth, is of a sufficient mechanical strength to maintain a desired shape without a supporting shell, and is substantially non-hardening and non-drying. To more closely approximate the actual characteristics of human flesh, the process allows for the injection of substances into the tissue simulating gel prior to it, just as these substances can be injected into actual tissue, and the tissue simulating gel is translucent, permitting the visual inspection of the interior. Application of a polyurethane spray often used for coating circuit boards provides a textured surface to the tissue simulating gel, making the tissue simulating gel easier to handle and contributing to its longevity.

The novelty consists of using substantially equal amounts of water and ethylene glycol, retaining water content in the final result, adding material to the tissue simulating gel to modify the electrical, sound conducting, and wave scattering properties of it, and coating the tissue simulating gel with a polyurethane spray to provide for an improved handling surface texture. The combination of these features makes the tissue simulating gel uniquely suitable in the field of hyperthermia medical research.

Inventors: John A. Companion
20-A Curtis Lane
Hampton, Virginia 23669
ss: [REDACTED]

Employer: PRC Kentron
Initial Evaluator: Fred Staggs

Serial No.: 07/418,372
Filed: October 6, 1989

TISSUE SIMULATING GEL FOR MEDICAL RESEARCHOrigin of the Invention

5 The invention described herein was made in the performance of work under a NASA contract and is subject to the provisions of Section 305 of the National Aeronautics and Space Act of 1958, Public Law 85-568 (72 Stat. 435; 42 USC 2457).

10 Background of the Invention1. Field of the Invention

15 This invention relates to a composition and a method for producing a tissue simulating gel. More specifically, the invention is a simulated soft human or animal tissue particularly applicable in the field of medical research because it will not melt at elevated temperatures, it is non-hardening and non-drying for extended periods of time, and it will not support bacterial growth.

20

2. Description of the Prior Art

25 Many formulae currently exist for producing tissue simulating gels. A number of these formulae are based on agars, simple hydrated collagen gels, or polyacrylimides. These formulae often suffer from deficiencies which make them ill-suited for extended medical research: hydrated gels tend to dry out; some gels melt at the elevated temperatures involved in research; others become hosts for micro-organisms; some are too expensive or too difficult to make
30 to be of practical value.

 Using a plasticizing agent such as ethylene glycol and a coagulating or precipitating agent such as formaldehyde in preparing

a substance which gives the appearance of flesh was described in U.S. 2,124,767 (Dawn). The invention disclosed in Dawn pertains primarily to the preparation of a masking substance used to disguise or change the appearance of an individual, particularly for acting purposes. The simulated flesh developed in Dawn is substantially dehydrated: it is prepared using ethylene glycol and water in proportions of approximately 2 to 1 respectively, following which the water is condensed out of the formulation using a pressure cooker. Dawn uses approximately 30 percent by weight of gelatin and less than 1 percent by weight of formaldehyde. One of the advantages of the Dawn formulation is its ability to withstand the heat of stage lights, though the formulation will melt and can be molded to an individual's skin using hot water.

Aside from appearance, the substance disclosed in Dawn has no other characteristics of human flesh, and it is therefore inappropriate for medical research. Unlike actual tissue, which is substantially water, the Dawn formulation after processing is substantially dehydrated. Furthermore, the Dawn formulation does not have the electrically conducting characteristic of actual tissue, nor does it have the sound conducting and wave scattering properties of actual tissue. Its ability to be melted with hot water while being molded to an individual's skin indicates it will not withstand the temperatures frequently encountered in hyperthermia research. Furthermore, because the Dawn formulation is produced using a pressure cooker, it is impractical to inject material into the substance to alter its properties before the substance sets. Once the substance has set, injection of any material will cause tearing.

Summary of the Invention

30

The present invention is a new composition of matter and a process for producing it.

An object of the present invention is to produce an animal or human tissue simulating gel that will be useful in medical research.

A further object of the present invention is a tissue simulating gel that does not melt at elevated temperatures experienced in hyperthermia research, does not dry-out nor harden for extended periods of time, and does not support the growth of micro-organisms.

A further object of the present invention is to provide a process for producing a tissue simulating gel such that before the gel sets, material can be injected or imbedded into it at such a point that the material will remain suspended in the tissue simulating gel once it sets, and the injection will not cause tearing of the tissue simulating gel.

To meet the foregoing objects, a tissue simulating gel and method for producing it have been developed. The new gel includes ethylene glycol, water, a cross-linking agent such as formaldehyde, and gelatin. Filler material and electrically conducting chemicals can be added to the gel to more closely approximate the characteristics of actual tissue. Glycerol can also be added to the mixture to give the tissue simulating gel a more rubbery characteristic which allows the gel to withstand handling somewhat better.

Initially, if desired, a soluble electrically conducting material is added to and dissolved in the water. It has been found that adding potassium chloride or sodium chloride is especially beneficial for this purpose. Next, about 80 grams to about 100 grams of gelatin is added to the water solution. It has been found that 100 grams of 175 to 300 Bloom gelatin per 1 liter of final solution of water and ethylene glycol works well, with 175 Bloom gelatin yielding a somewhat softer tissue simulating gel. The ethylene glycol is then added to the water solution in a proportion to water which is between 50 to 50 and 65 to 35. Using substantially equal amounts

of ethylene glycol and water has been found to be especially beneficial. At this point, the mixture is heated and stirred continuously to melt the gelatin. As soon as the gelatin melts, the mixture is removed from the heat. The material then can be
5 deaerated and stored. If the material is stored, it will solidify, and will need to be remelted before adding the cross-linking agent. The cross-linking agent is added in an amount equivalent to between about 20 grams and about 40 grams of formaldehyde per 1 liter of ethylene glycol and water solution. It has been found to be
10 especially preferred to use about 75 milliliters of a 37% aqueous solution formaldehyde per 1 liter of solution of water and ethylene glycol. The pot life of the mixture after the cross-linking agent has been added is highly dependent on the temperature of the solution at the time the cross-linking agent is added. If the solution is hot
15 when the cross-linking agent is added, the gel will set-up within a few seconds. Therefore, it is more desirable to add the cross-linking agent after the mixture has cooled. If the cross-linking agent is added when the solution is cooled to a temperature just above the temperature at which the solution would normally set
20 (approximately 32°C), the pot life will be about 55-60 minutes.

Once the viscosity of the solution has reached a point at which it will suspend particles, filler material may be added to mimic the sound conducting and wave scattering properties of a particular type of tissue being simulated. Typically, the mixture will reach the
25 desired viscosity during the last ten of the sixty minutes during which the gel sets.

The tissue simulating gel, during the viscous phase, has a sticky characteristic viscous enough to allow the insertion of hypodermic needles and catheters without tearing. Moreover, the
30 resulting tissue simulating gel is translucent, allowing visual inspection of the interior. A polyurethane coating can be sprayed on or applied to the tissue simulating gel to give it the texture of

skin and increase the longevity thereof by further protecting it from dehydration. The tissue simulating gel is especially suitable for hyperthermia medical research: it is non-hardening and non-drying for extended periods of time, and it will not melt at the elevated
5 temperatures involved in such research. Furthermore, the tissue simulating gel will not support the growth of micro-organisms.

Description of the Preferred Embodiment

10 The present invention is a new composition of a tissue simulating gel and a method for producing it.

Hyperthermia cancer research often requires a simulated tissue to conduct electricity in order for microwaves, which are used to produce the hyperthermia, to react with the simulated tissue in the
15 same manner as they would react with actual tissue. Therefore, if the particular research for which the tissue simulating gel will be used requires the tissue simulating gel to conduct electricity, the first step of the process is to dissolve enough sodium chloride into about 0.5 liters of distilled water to give the tissue simulating gel
20 the dielectric constant of a particular body tissue being simulated. One-hundred grams of gelatin is then added to the solution. The gelatin should be added to the water when the water is cold (room temperature or below) to prevent lumping which results from adding the gelatin to hot water. A 175 Bloom gelatin is preferred over
25 higher Bloom gelatins because the 175 Bloom gelatin yields a slightly softer characteristic in the final tissue simulating gel than higher Bloom gelatins.

Next, about 0.5 liters of ethylene glycol is added to and stirred into the mixture. Also, about 100 milliliters of glycerol per liter of
30 solution of water and ethylene glycol can be added to impart a rubbery characteristic on the tissue simulating gel.

The mixture is heated slowly to about 38° to 45° C while it is

stirred constantly. The temperature of the mixture is maintained and the mixture is stirred until all the gelatin is dissolved.

As soon as the gelatin is completely dissolved, the solution should be removed from the heat in order to prevent water loss.

- 5 The solution is then deaerated. Deaerating can be accomplished most easily by setting the mixture aside until all the air bubbles come to the surface and can be skimmed off. A more effective way to deaerate, however, is to use a vacuum pump, placing the solution under a partial vacuum. At this point, the material can be stored.
- 10 Storing can often times be accomplished most easily in a covered plastic container. If stored, however, the material will solidify, but it can easily be remelted when needed by applying heat.

- The next step in the process is to catalyze the material in its liquid state. Catalyzation is best accomplished when the solution is
- 15 cooled to below 38° C but above a temperature at which it begins to solidify (typically at 32° C or below). This catalyzation is most easily accomplished by adding to the tissue simulating solution 100 milliliters of 37 percent formaldehyde solution per liter quantity of aqueous solution of ethylene glycol. The formaldehyde must be
- 20 mixed thoroughly into the tissue simulating gel solution, and then the tissue simulating solution is poured into a mold. Generally when using 175 Bloom gelatin, the working life of the tissue simulating gel before it sets-up is approximately 60 minutes, although the working life is somewhat shorter when using higher Bloom gelatins.

- 25 During approximately the last ten minutes of the working life of the tissue simulating gel after catalyzation, the tissue simulating gel enters a viscous state during which various filler and other material can be imbedded into the tissue simulating gel and remain suspended in the tissue simulating gel after it sets-up. Examples
- 30 of such imbedded materials include simulated tumors, cell wall simulating additives, or thermometry devices. A hypodermic needle can be used at this point to inject materials; after injection, the hole

through which the needle passed will close. Proprietary wax compounds intended for hyperthermia cancer research can also be imbedded during this stage.

5 After the cross-linking has taken place and the tissue simulating gel has completely set-up, it can be removed from the mold and used without any supporting shell.

Sometimes it may be desired to apply a polyurethane coating to the surface of the gel to give the gel a texture similar to skin.

What is claimed is:

TISSUE SIMULATING GEL FOR MEDICAL RESEARCHAbstract of the Disclosure

5 A tissue simulating gel and a method for preparing the tissue
simulating gel are disclosed. The tissue simulating gel is prepared
by a process using water, gelatin, ethylene glycol, and a cross-
linking agent. In order to closely approximate the characteristics of
10 the type of tissue being simulated, other material has been added
to change the electrical, sound conducting, and wave scattering
properties of the tissue simulating gel. The result of the entire
process is a formulation that will not melt at the elevated
temperatures involved in hyperthermia medical research.
5 Furthermore, the tissue simulating gel will not support mold or
bacterial growth, is of a sufficient mechanical strength to maintain
a desired shape without a supporting shell, and is non-hardening
and non-drying. Substances have been injected into the tissue
simulating gel prior to the setting-up thereof just as they could be
10 injected into actual tissue, and the tissue simulating gel is
translucent so as to permit visual inspection of its interior. A
polyurethane spray often used for coating circuit boards can be
applied to the surface of the tissue simulating gel to give a texture
similar to human skin, making the tissue simulating gel easier to
15 handle and contributing to its longevity.